PD CEN/TR 16988:2016

BSI Standards Publication

Estimation of uncertainty in the single burning item test

bsi.

National foreword

This Published Document is the UK implementation of CEN/TR 16988:2016.

The UK participation in its preparation was entrusted to Technical Committee FSH/21, Reaction to fire tests.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

ISBN 978 0 580 90291 8

ICS 17.200.01

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 August 2016.

Amendments issued since publication

Date	Text affected

TECHNICAL REPORT

RAPPORT TECHNIQUE

TECHNISCHER BERICHT

CEN/TR 16988

July 2016

ICS 17.200.01

English Version

Estimation of uncertainty in the single burning item test

Messunsicherheit - Thermische Beanspruchung durch einen einzelnen brennenden Gegenstand (SBI)

This Technical Report was approved by CEN on 4 July 2016. It has been drawn up by the Technical Committee CEN/TC 127.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Ref. No. CEN/TR 16988:2016 E

Contents

Page

European foreword

This document (CEN/TR 16988:2016) has been prepared by Technical Committee CEN/TC 127 “Fire Safety in Buildings”, the secretariat of which is held by BSI.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

1 Scope

1.1 General

The measuring technique of the SBI (single burning item) test instrument is based on the observation that, in general, the heats of combustion per unit mass of oxygen consumed are approximately the same for most fuels commonly encountered in fires (Huggett [12]). The mass flow, together with the oxygen concentration in the extraction system, suffices to continuously calculate the amount of heat released. Some corrections can be introduced if CO_2, CO and/or H_2O are additionally measured.

1.2 Calculation procedure

1.2.1 Introduction

The main calculation procedures for obtaining the HRR and its derived parameters are summarized here for convenience. The formulas will be used in the following clauses and especially in the clause on uncertainty.

The calculations and procedures can be found in full detail in the SBI standard [1].

1.2.2 Synchronization of data

The measured data are synchronized making use of the dips and peaks that occur in the data due to the switch from 'primary' to 'main' burner around t = 300 s, i.e. at the start of the thermal attack to the test specimen. Synchronization is necessary due to the delayed response of the oxygen and carbon dioxide analysers. The filters, long transport lines, the cooler, etc. in between the gas sample probe and the analyser unit, cause this shift in time.

After synchronization, all data are shifted so that the 'main' burner ignites – by definition – at time t = 300 s.

1.2.3 Heat output

1.2.3.1 Average heat release rate of the specimen (HRR_{30s})

A first step in the calculation of the HRR contribution of the specimen is the calculation of the global HRR. The global HRR is constituted of the HRR contribution of both the specimen and the burner and is defined as

$$\mathrm{HRR}_{\mathrm{total}}(t) = E' \dot{V}_{D298}(t) x_{\mathrm{a\_O2}} \left(\frac{\phi(t)}{1 + 0{,}105\phi(t)} \right) \tag{1}$$

where

$\mathrm{HRR}_{\mathrm{total}}(t)$ is the total heat release rate of the specimen and burner (kW);

E' is the heat release per unit volume of oxygen consumed at 298 K, = 17 200 (kJ/m3);

$\dot{V}_{D298}(t)$ is the volume flow rate of the exhaust system, normalized at 298 K (m3/s);

$x_{\mathrm{a\_O2}}$ is the mole fraction of oxygen in the ambient air including water vapour;

$\varphi(t)$ is the oxygen depletion factor.

The last two terms $x_{\mathrm{a\_O2}}$ and $\left(\frac{\phi(t)}{1 + 0{,}105\phi(t)} \right)$ express the amount of moles of oxygen, per unit volume, that have chemically reacted into some combustion gases. Multiplication with the volume flow gives the