



BSI Standards Publication

# **Cast irons — Determination of non-combined carbon content — Infrared absorption method after combustion in an induction furnace**

**National foreword**

This Published Document is the UK implementation of ISO/TS 10719:2016.

The UK participation in its preparation was entrusted to Technical Committee ISE/102, Methods of Chemical Analysis for Iron and Steel.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.

Published by BSI Standards Limited 2016

ISBN 978 0 580 90632 9

ICS 77.080.10

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 December 2016.

**Amendments/corrigenda issued since publication**

Date	Text affected
------	---------------

---

# TECHNICAL SPECIFICATION

**ISO/TS**  
**10719**

First edition  
2016-12-01

---

---

## **Cast irons — Determination of non-combined carbon content — Infrared absorption method after combustion in an induction furnace**

*Fontes — Détermination du carbone non combiné — Méthode par absorption dans l'infrarouge après combustion dans un four à induction*



Reference number  
ISO/TS 10719:2016(E)

© ISO 2016



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
[copyright@iso.org](mailto:copyright@iso.org)  
[www.iso.org](http://www.iso.org)

# Contents

Page

<b>Foreword</b>	<b>iv</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>1</b>
<b>4 Principle</b>	<b>1</b>
<b>5 Reagents</b>	<b>2</b>
<b>6 Apparatus</b>	<b>2</b>
<b>7 Sampling</b>	<b>3</b>
<b>8 Procedure</b>	<b>3</b>
8.1 General operating instructions	3
8.2 Test portion	4
8.3 Blank test	4
8.4 Determination	4
8.4.1 Dissolution of the test portion	4
8.4.2 Filtration of the non-combined carbon	4
8.4.3 Measurements	4
8.5 Establishing the calibration curve	5
8.5.1 Primary product calibration	5
8.5.2 Calibration by means of certified reference materials	5
<b>9 Expression of results</b>	<b>6</b>
9.1 Primary product calibration	6
9.2 Calibration by means of certified reference materials	6
<b>10 Precision</b>	<b>6</b>
<b>11 Notes on the procedure</b>	<b>7</b>
11.1 Preliminary blank tests	7
11.2 Preliminary tests on certified reference materials	7
<b>12 Test report</b>	<b>7</b>
<b>Annex A (informative) Additional information on the international interlaboratory test</b>	<b>8</b>
<b>Annex B (informative) Comparison between the results of the first and the second precision tests</b>	<b>10</b>
<b>Annex C (informative) Effect of fine material in a sample on the determination of non-combined carbon content</b>	<b>11</b>
<b>Bibliography</b>	<b>14</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

The committee responsible for this document is ISO/TC 17, *Steel*, Subcommittee SC 1, *Methods of determination of chemical composition*.

This first edition Technical Specification replaces the first edition Technical Report (ISO/TR 10719:1994), which has been technically revised. The following changes have been made:

- steels have been deleted from the scope;
- the possibility to establish the calibration curve by means of certified reference materials has been added;
- assessment of the precision data has been revised.

# Cast irons — Determination of non-combined carbon content — Infrared absorption method after combustion in an induction furnace

## 1 Scope

This document specifies an infrared absorption method after combustion in an induction furnace for the determination of non-combined carbon content in cast irons.

The method is applicable to non-combined carbon contents between 1,0 % (mass fraction) and 3,0 % (mass fraction).

Elements ordinarily present do not interfere. However, some alloyed cast irons, when extensively heat treated, contain carbides that are not soluble when using this method and may give high values for non-combined carbon.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

### 3.1

#### **non-combined carbon**

graphitic carbon

carbon that is not dissolved by methanol and nitric and hydrofluoric acids

## 4 Principle

Decomposition of a test portion with nitric acid in the presence of methanol and treatment with hydrofluoric acid. Removal of the non-combined carbon by filtering through a glass-fibre filter.

Combustion of the glass-fibre filter containing the non-combined carbon in a flow of oxygen at a high temperature, using a high-frequency induction furnace, in the presence of pure iron and an accelerator. Transformation of carbon into carbon dioxide and/or carbon monoxide.

Measurement by infrared absorption of the carbon dioxide and/or carbon monoxide, carried by the current of oxygen.