

PD ISO/TS 19022:2016



BSI Standards Publication

Plastics — Method of controlled acceleration of laboratory weathering by increased irradiance

National foreword

This Published Document is the UK implementation of ISO/TS 19022:2016.

The UK participation in its preparation was entrusted to Technical Committee PRI/21, Testing of plastics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.

Published by BSI Standards Limited 2016

ISBN 978 0 580 86183 3

ICS 83.080.01

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 29 February 2016.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

TECHNICAL SPECIFICATION

**ISO/TS
19022**

First edition
2016-02-01

Plastics — Method of controlled acceleration of laboratory weathering by increased irradiance

*Plastiques — Méthode d'accélération contrôlée du vieillissement en
laboratoire par irradiance accrue*



Reference number
ISO/TS 19022:2016(E)

© ISO 2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and abbreviated terms	2
5 Principle	2
6 Apparatus	2
6.1 General	2
6.2 Test chamber	2
6.3 Laboratory radiation source	3
6.3.1 General	3
6.3.2 Spectral irradiance	3
6.3.3 Irradiance uniformity	3
6.4 Radiometer	4
6.5 Test chamber temperature and relative humidity	4
6.6 Black-standard/black-panel thermometer	4
6.7 Wetting and humidity-control equipment	4
6.7.1 General	4
6.7.2 Relative-humidity control equipment	4
6.7.3 Spray system	4
6.8 Specimen holders	4
6.9 Apparatus to assess changes in properties	5
7 Test specimens	5
8 Test method	5
9 Exposure conditions	6
9.1 Radiation	6
9.2 Temperature	6
9.2.1 Black-standard and black-panel temperature	6
9.2.2 Chamber air temperature	6
9.2.3 Specimen surface temperature	6
9.3 Humidity of chamber air	7
9.3.1 Relative humidity of chamber air	7
9.3.2 Spray cycle	7
10 Procedure	7
10.1 General	7
10.2 Mounting the test specimens	7
10.3 Exposure	7
10.4 Measurement of radiant exposure	8
10.5 Determination of changes in properties after exposure	8
11 Test report	8
Annex A (informative) Principle of reciprocity	9
Bibliography	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#).

The committee responsible for this document is ISO/TC 61, *Plastics*, Subcommittee SC 6, *Ageing, chemical and environmental resistance*.

Introduction

A realization of the acceleration of laboratory weathering under controlled conditions is an essential requirement for delivering reliable and fast prediction of material durability. In this connection, the correlation to real use aging behaviour is being checked constantly.

The fundamental parameters of a weathering test are simulated solar radiation, heat and moisture. The induced change in the material properties, among other things, is determined by the irradiance level and relative spectral irradiance of simulated solar radiation incident on the material surface during the test, the surface temperature, and the level of moisture. An increase in some well-known weather parameters, continuously monitored outdoors, offers opportunities to speed up the weathering process outdoors and in the laboratory. Since 1967, acceleration of outdoor weathering with instruments for intensified weathering using concentrated solar radiation (according to ISO 877-3) became a common practice. By concentrating the natural solar radiation with Fresnel mirrors, irradiances of five to six times higher than the maximum natural level has been reached. Already in 1996, a screening procedure with very high irradiances for dyed textiles were developed which enabled the reduction of the test duration for lightfastness grades from five days to seven days to two and a half days. [5]

However, the applicability of an increased irradiance for deterministic acceleration of weathering without a specific knowledge of material properties requires that the degradation of material (at constant temperature and moisture conditions) has to be dependent on the applied radiant exposure only, irrespective of the irradiance level and resulting exposure duration used during the test. For some materials fulfilling this criterion, the acceleration of weathering has been demonstrated successfully. [6][7][8][9] This criterion is not always fulfilled since an increase in the irradiance might not always produce the expected increase in the weathering acceleration due to possible and a priori unknown to the operator nonlinear dependence of the photochemical processes on the irradiance level. Moreover, the overall material degradation might be strongly affected by the other weather parameters which can be modified due to the increased irradiance.

There are limitations in using increased irradiances. Therefore, the applicability and the limits of this weathering acceleration approach are determined by the properties of the specific material and have to be investigated systematically in each particular case. In this respect, it is of essential importance to validate an appropriate test procedure under controlled conditions in laboratory with an artificial radiation source which can provide high irradiances above the natural level with the relative spectral irradiance closely mimicking the natural solar radiation. Simultaneously, the temperature of the sample specimen surface and of the chamber air is kept constant in a wide range of irradiance level. In addition, the usual wetting and rain option have to be available.

Plastics — Method of controlled acceleration of laboratory weathering by increased irradiance

1 Scope

This Technical Specification specifies a test method which allows predicting the aging rate of material specimens, e.g. plastics, under interest independent of the aging mechanisms as a function of radiant exposure. The UV irradiance of a simulated solar radiation (with a laboratory radiation source) will be extended above the normal maximum level on earth surface while keeping all relevant temperature parameters fixed.

NOTE For translucent plastics, the surface temperatures are below the white standard temperature. In addition, the maximum temperature is not on the irradiated surface, it is somewhere inside the plastic material.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4582, *Plastics — Determination of changes in colour and variations in properties after exposure to daylight under glass, natural weathering or artificial light*

ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance*

ISO 9370, *Plastics — Instrumental determination of radiant exposure in weathering tests — General guidance and basic test method*

ISO 10640, *Plastics — Methodology for assessing polymer photo ageing by FT-IR and UV-visible spectrometry*

ISO/TR 17801, *Plastics — Standard table for reference global solar spectral irradiance at sea level — Horizontal, relative air mass 1*

CIE Publication No. 85:1989, *Solar spectral irradiance*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

radiant exposure

H

radiant energy per unit

Note 1 to entry: Radiant exposure is given by the following formula:

$$H = \int E \times dt$$

where

E is the irradiance, in watts per square metre ($\text{W} \times \text{m}^{-2}$);

t is the exposure time, in seconds (s).

Note 2 to entry: H is therefore expressed in joules per square metre ($\text{J} \times \text{m}^{-2}$).